

# CP350

## URETHANE BASE COAT



### KEY BENEFITS SUMMARY

- Highly elastomeric liquid-applied waterproofing membrane with excellent crack bridging properties
- Fully bonded to substrate - prevents water ingress
- Rapid curing - can be overcoated in as little as 6 hours

### PRODUCT INFORMATION

#### Description

CP350 is a next generation, self levelling rapid curing polyurethane waterproofing membrane, typically mixed with water. Not suitable as the final wearing surface, must be over-coated with a suitable sealer such as CP951 Urethane Sealer.

#### Uses

CP350 can be used either as part of a TREMCO CP Urethane waterproofing system, or as a stand-alone waterproof membrane. Typical applications include car parks, balconies, walkways, plant rooms, roofs and similar installations.

#### Packaging

18.9 litres

#### Colour

Grey

#### Availability

Direct from tremco illbruck (see back of leaflet for address and telephone details).

#### Application

CP350 is typically mixed with 500 ml water/unit to accelerate curing although certain applications may not require any water – refer to project instructions for details on this and for general application instructions. Contact tremco illbruck for full details.

### Health & Safety Precautions

Safety data sheet must be read and understood before use.

### Technical Service

tremco illbruck has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

### Guarantee / Warranty

tremco illbruck products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with tremco illbruck written instructions and (b) in any application recommended by tremco illbruck, but which is proved to be defective, will be replaced free of charge.

No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct.

tremco illbruck Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.

### TECHNICAL DATA

PROPERTY	RESULT
Composition	CP350 is a polyurethane based moisture curing system, typically mixed with water.
Specific Gravity (@ +20°C)	1.28
Pot Life (@ +20°C)	4 hours
Max Tensile Stress	2.2 MPa
Elongation at Break	1040%
Storage	Store in dry shaded conditions between +5°C and +25°C.
Shelf Life	12 months when stored as recommended in original unopened packaging.