

CP191

URETHANE PU RE-ACTIVATOR



KEY BENEFITS SUMMARY

- Fast drying
- Moisture curing single pack
- For over-coating existing PU coatings

PRODUCT INFORMATION

Description

CP191 is a quick drying 1-part moisture curing primer.

Uses

CP191 is used to prepare surfaces of cured polyurethane coatings and sealants prior to application of TREMCO CP urethane coatings.

Packaging

18.9 litres

Colour

Clear

Availability

Direct from tremco illbruck (see back of leaflet for address and telephone details).

Protective Equipment

USE IN WELL VENTILATED CONDITIONS and ensure all recommended protective equipment is worn during handling & use of this product. For full recommendation, refer to safety data sheet.

Method of Application

Refer to project-specific instructions for details of application procedures. Contact tremco illbruck for full details. Please refer to the overcoating times (table attached on the second page).

Health & Safety Precautions

Safety data sheet must be read and understood before use.
 Flammable - keep away from open flames and other ignition sources.

Technical Service

tremco illbruck has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

Guarantee / Warranty

tremco illbruck products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with tremco illbruck written instructions and (b) in any application recommended by tremco illbruck, but which is proved to be defective, will be replaced free of charge.

No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct.

tremco illbruck Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.

TECHNICAL DATA

PROPERTY	RESULT
Composition	A one part, solvent based polyurethane
Specific Gravity	0.899
Pot Life (at +20°C)	6 hours
Storage	Store in dry shaded conditions between +5°C and +25°C
Shelf Life	12 months when stored as recommended in original unopened containers

PRIMER TACK AND OPEN TIMES

Temperature (°C)	Tack Time	Open Time (after primer has reached tack)
4 to 10	1.5 - 2 hours	1 hour
10 to 15	1 - 1.5 hours	45 - 60 minutes
15 to 24	30 minutes - 1 hour	20 - 45 minutes
24 to 32	10 minutes - 30 minutes	10 - 20 minutes
Above 32	Proceed with caution	

