

# CP500

## MMA FILLER



### KEY BENEFITS SUMMARY

- Improves characteristics of finished flooring
- Easily dispersed in TREMCO MMA Resins
- Suitable for poured, raked and rolled systems

### PRODUCT INFORMATION

#### PRODUCT INFORMATION

##### Description

CP500 is a light grey, medium grade free flowing powder for use as a filler with TREMCO MMA Resins.

##### Usage / Purpose

CP500 improves the performance and characteristics of TREMCO MMA Coating Systems.

##### LIMITATIONS

Over addition of fillers can result in reduced life of the TREMCO MMA Coating Systems, always use the specified filler to resin ratio.

##### Colour

Light grey

##### Packaging

CP500 Filler: 25 kg bags

##### Availability

Direct from tremco illbruck (see back of leaflet for address and telephone details).

##### Standards

For flooring applications, all aspects of the installation must be in accordance with the requirements of BS8204 and supplementary specifications.

##### Protective Equipment

Use in well ventilated conditions and ensure all recommended protective equipment is worn during handling & use of this product. For full recommendation, refer to safety data sheet.

#### Method of Application

CP500 Filler should be thoroughly mixed with the TREMCO MMA Resin to achieve an even distribution.

##### ADDITION OF CP500

- CP500 should be added to the TREMCO MMA Resin at the specified filler to resin ratio.
- CP500 should be added to the TREMCO MMA Resin after the addition of CP510 Initiator to ensure there is an even dispersion of CP510 Initiator.

#### Health & Safety Precautions

Safety data sheet must be read and understood before use.

#### Technical Service

tremco illbruck has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

#### Guarantee / Warranty

tremco illbruck products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with tremco illbruck written instructions and (b) in any application recommended by tremco illbruck, but which is proved to be defective, will be replaced free of charge. No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct.

tremco illbruck Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.

## TECHNICAL DATA

PROPERTY	RESULT
Composition	A light grey quartz powder
Density (DIN 51757 at +20°C)	2.65 g/cm <sup>3</sup>
Melting Point	1700°C
pH	6 - 7
Coverage	Approximately 2.4 kg/m <sup>2</sup> depending on system applied and application method
Storage	Store in cool, dry, shaded conditions between +5°C and +35°C
Shelf Life	12 months when stored in dry conditions in original unopened containers

