

CP120 AlphaGuard® Primer

URETHANE REACTIVATION PRIMER



KEY BENEFITS SUMMARY

- Quick drying
- Enhanced adhesion

PRODUCT INFORMATION

Description

CP120 is a single component primer designed to enhance adhesion when using TREMCO urethane products including AlphaGuard and urethane sealants.

Usage / Purpose

CP120 is utilised to promote adhesion of cured urethane coatings and sealants to newly applied coats. It can also be used as primer over approved substrates. To determine if a substrate is approved, reference current TREMCO literature or contact TREMCO Technical Services.

Packaging

Available in 18.9 litre containers.

Colour

Pale Yellow

Availability

Direct from tremco illbruck (see bottom of leaflet for address and telephone details).

Protective Equipment

USE IN WELL VENTILATED CONDITIONS and ensure all recommended protective equipment is worn during handling & use of this product. For full recommendation, refer to safety data sheet.

Surface Preparation

- All surfaces are to be free of dirt, grease, oil, chalk, loose paint, rust, mortar, and other foreign matter, which could prevent proper adhesion.
- This is best accomplished by power washing or utilising a stiff broom.
- All surfaces must be completely dry prior to the application of CP120.

Application Method

- Brush, roller or spray

Application

- Apply primer evenly on surface at the recommended coverage rate. Do not allow the product to puddle.
- Once the primer becomes dry and tacky (typically 15-30 minutes) it can be top coated.
- Primer must be top coated prior to curing hard, glossy, and tack-free (typically within 1-2 hours). If this occurs, clean the primed area and re-prime following the application instructions listed above.

Cleaning

Clean equipment with xylene. Any spills or over-coating must be cleaned immediately before CP120 dries.

Please Note

- Apply only when ambient temperatures are 5°C and rising.
- Do not apply over wet or damp surfaces or when precipitation is imminent.
- Only apply over approved substrates and products.
- Exposed primer will yellow as it weathers.

Health & Safety Precautions

Safety data sheet must be read and understood before use.

CP120 AlphaGuard® Primer

URETHANE REACTIVATION PRIMER

TREMCO

Technical Service

tremco illbruck has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

Guarantee / Warranty

tremco illbruck products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with tremco illbruck written instructions and (b) in any application recommended by tremco illbruck, but which is proved to be defective, will be replaced free of charge. No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct.

tremco illbruck Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.

TECHNICAL DATA

PROPERTY	RESULT
Weight per litre (ASTM D 1475)	1.24 kg
Viscosity (ASTM D 562)	20-50 CPS (mPas)
Flash Point (ASTM D 3278)	43°C
Dry Time	15 - 30 minutes at 21°C
Coverage	9.8 m ² /l
Storage	Store in dry shaded conditions between +15°C and +26°C and low humidity. Storage temperatures must not exceed 43°C. Do not store in direct sunlight.
Shelf Life	12 months when stored as recommended in original unopened packaging

