

# CP130 AlphaGuard® M-Prime

## NON-POROUS SURFACE PRIMER



### KEY BENEFITS SUMMARY

- Quick Drying
  - Apply coating or sealant the same day
- Excellent Adhesion to
  - Allows for excellent metals and plastics bond of urethane coatings and sealants

### PRODUCT INFORMATION

#### Description

CP130 is a low-VOC, water-based, quick-drying, one-part primer. AlphaGuard M-Prime is used as an adhesion promoter for urethane sealants and coatings on non-porous surfaces such as metal and plastics.

#### Usage / Purpose

CP130 is designed for use on galvanized steel, aluminium, anodized aluminium, copper and PVC prior to the application of TREMCO urethane sealants and coatings.

#### Packaging

Available in 3.78 litre containers.

#### Colour

Red

#### Availability

Direct from tremco illbruck (see bottom of leaflet for address and telephone details).

#### Protective Equipment

USE IN WELL VENTILATED CONDITIONS and ensure all recommended protective equipment is worn during handling & use of this product. For full recommendation, refer to safety data sheet.

#### Surface Preparation

- Surfaces must be clean, dry, and free from oil and other contaminants.
- Clean surfaces using appropriate solvent or cleaner, depending on the substrate. Mask off areas adjacent to where CP130 will be applied to prevent staining.
- Surfaces such as milled aluminium, copper, and rusted metal must be abraded to a bright metal finish prior to applying AlphaGuard M-Prime.

#### Application Method

- Brush or roller

#### Application

- Apply CP130 in a continuous film. Normal drying time is approximately 15 minutes. Drying time will be extended under cool weather conditions. CP130 must be completely dry before applying sealant or coating.
- Urethane sealants and coatings can be applied up to 8 hours after CP130 has been applied. After 8 hours, the surface must be cleaned with MEK or xylene and re-primed with CP130.

#### Cleaning

Clean equipment with ethyl alcohol. Any spills or over-coating must be cleaned immediately before CP130 dries.

#### Please Note

- CP130 can discolour surfaces to which it is applied. Mask off adjacent areas to prevent staining.

#### Health & Safety Precautions

Safety data sheet must be read and understood before use.

# CP130 AlphaGuard® M-Prime

## NON-POROUS SURFACE PRIMER

**TREMCO**

### Technical Service

tremco illbruck has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

### Guarantee / Warranty

tremco illbruck products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with tremco illbruck written instructions and (b) in any application recommended by tremco illbruck, but which is proved to be defective, will be replaced free of charge. No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct.

tremco illbruck Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.

### TECHNICAL DATA

PROPERTY	RESULT
Composition	Water-based primer
Density (25°C) ASTM D1475-90	1 kg/l
Asbestos Content (ASTM D276-87)	None
Storage	Store in dry shaded conditions between +15°C and +26°C and low humidity. Storage temperatures must not exceed 43°C. Do not store in direct sunlight.
Shelf Life	12 months when stored as recommended in original unopened packaging



tremco illbruck Limited, Coupland Rd,  
Hindley Green, Wigan, WN2 4HT, UK.  
Tel: +44 (0)1942 251400  
Fax: +44 (0)1942 251410  
Email: [uk.info@tremco-illbruck.com](mailto:uk.info@tremco-illbruck.com)  
Website: [www.tremco-illbruck.co.uk](http://www.tremco-illbruck.co.uk)



[www.tremco-illbruck.com](http://www.tremco-illbruck.com)

2019-02