

# CP930

## MMA WATERPROOF SEALER



### KEY BENEFITS SUMMARY

- Easy to apply
- Fast curing
- Semi-flexible
- Weather resistant
- Based on PUMA technology-free from external plasticiser

### PRODUCT INFORMATION

#### Description

CP930 is a medium viscosity, flexible and UV protected surface sealer based on acrylic resins. The curing is initiated by addition of CP510 MMA Initiator.

#### Usage / Purpose

CP930 is used as a surface sealer for TREMCO MMA waterproofing systems to improve general resistance and maintenance properties.

#### Packaging

20 kg units

#### Colour

CP930 MMA Waterproof Sealer: Neutral

CP510 Initiator: White powder

CP592 Pigment:

Standard colours available:

Anthracite Grey	-	RAL 7016
Dusty Grey	-	RAL 7037
Traffic Green	-	RAL 6024
Traffic Red	-	RAL 3020
Traffic Blue	-	RAL 5017

A full range of colours is available to suit project requirements (minimum order quantities apply).

#### Availability

Direct from Tremco CPG UK Limited (see bottom of leaflet for address and telephone details).

#### Protective Equipment

USE IN WELL VENTILATED CONDITIONS and ensure all recommended protective equipment is worn during handling & use of this product. For full recommendation, refer to safety data sheet.

#### Surface preparation

- The TREMCO MMA system to be sealed must be dry, clean, free from dust and grease.
- Any fresh base coat must be completely cured.
- For broadcast systems all loose aggregate or flakes must be thoroughly removed prior to applying the CP930.

#### Mixing

- Prior to use, CP930 must be carefully stirred to achieve a uniform distribution of the paraffin and fillers contained in the product.
- Add 10% by weight, or as otherwise directed by Tremco CPG UK Limited technical services, CP592 micronised pigment in the required colour and mix thoroughly until uniformly distributed.
- CP930 is thoroughly mixed together with the CP510 MMA Initiator (50% dibenzoyl peroxide), in accordance with the below guidelines.
- Ensure the product is mixed using a suitable non-sparking/ATEX mixer.

It should be noted that the amount of catalyst powder to be added depends upon the temperature.

Temperature	Catalyst to add to each 22 kg
30°C	180 g
20°C	360 g
10°C	540 g
0°C	720 Kg

For eventual addition of filler or pigment on site, please contact our Technical Service Department for further details.

#### Note:

Weight to Volumetric conversion of Catalyst.  
1 cm<sup>3</sup> of CP510 MMA Initiator = 0.64 g  
1 g of CP510 MMA Initiator = 1.57 cm<sup>3</sup>

#### Method of Application

- Immediately after the catalyst has been added and mixed, the sealer is spread onto the CP215 MMA Base Coat using a rubber squeegee and paint roller.
- For good results it is important always to work with freshly catalyzed material (i.e. small batch sizes).
- Layer thickness must be kept within 0.6-0.8kg/m<sup>2</sup> on aggregated surfaces, 0.3-0.7kg/m<sup>2</sup> on non-aggregated surfaces.

# CP930

## MMA WATERPROOF SEALER

TREMCO

### Cleaning

Clean tools, etc., and remove surplus material using AW421 cleaner.

### Health & Safety Precautions

Safety data sheet must be read and understood before use.  
Highly flammable - keep away from open flames and other ignition sources.

### Technical Service

Tremco CPG UK Limited has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

### Guarantee / Warranty

Tremco CPG UK Limited products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with Tremco CPG UK Limited written instructions and (b) in any application recommended by Tremco CPG UK Limited, but which is proved to be defective, will be replaced free of charge.

No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct.

Tremco CPG UK Limited Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.

### TECHNICAL DATA

PROPERTY	RESULT (Typical Values for Pigmented CP930)
Composition	Modified MMA resin
Viscosity (DIN 53018 @ 25°C)	190 - 270 mPa*s
Density (ISO 2811 @ 25°C)	1.10 g/ml
Pot Life/Processing Time (@25°C)	Approximately 15 minutes
Curing Time (@ 25°C)	Approximately 60 minutes
Flash Point (ISO 1516)	+11.5°C
PROPERTY	RESULT (Cured State)
Tensile Strength (ISO 527)	13.5 MPa
Elongation (ISO 527)	85%
Elongation At Maximum Strength (ISO 527)	6.9 %
Shore D Hardness (DIN 53505)	55
Abrasion Taber 500 Cycles	51 mg
Modulus Of Elasticity (ISO 527)	345 MPa
Coverage	Consumption of CP930 depends on the system and varies up to 0.8 kg per m <sup>2</sup>
Storage	Store in dry, shaded conditions between +10°C and +20°C
Shelf Life	6 months when stored as recommended in original unopened containers

Please note that an objective comparison with other data is only possible if norms and parameters are identical.



Tremco CPG UK Limited  
Coupland Rd, Hindley Green, Wigan WN2 4HT  
United Kingdom  
Tel: +44 (0)1942 251400  
Email: info.UK@cpgeurope.com

CPG Construction Products Group Europe  
www.cpg-europe.com

2021-03